


Derprosa™
by Taghleef Industries

Derprosa™ Gloss Antimicrobial



derprosa.com
ti-films.com

Gloss film with antiviral
and antibacterial properties





15F138 Gloss Antimicrobial Wet
24F238 Gloss Antimicrobial Thermal
24D238 Gloss Antimicrobial Digi-Stick

Gloss film with antiviral and antibacterial properties
Film brillo con propiedades antiviricas y antibacterianas

Main features

Características principales

BOPP BOPP	Transparent Transparente	Gloss Brillo	Antimicrobial Antimicrobial	Food contact approved OK contacto alimenticio	Glueable Hot-Melt Colable Hot-Melt	Stampable standard design Estampable básico	Wet Al frío, sin adhesivo	Thermal Termo	Thermal digital & offset Termo digital & offset

Special features

Características destacadas

- * Antiviral. It reduces coronavirus SARS-CoV-2 presence by 84% after 24 hours*
- * Antibacterial. It reduces bacteria presence by 99% after 24 hours*
- * Tests carried out by independent laboratories according to ISO 21702 and 22196
- * Same gloss finish, excellent contact clarity and properties as Derprosa™ Gloss Premier
- * *Antivirus. Reduce la presencia de coronavirus SARS-CoV-2 un 84% tras 24 horas**
- * *Antibacterias. Reduce la presencia de bacterias un 99% tras 24 horas**
- * *Test realizados por laboratorios independientes según ISO 21702 e ISO 22196*
- * *Mismo acabado brillo, excelente claridad y propiedades mecánicas que Derprosa™ Gloss Premier*

Typical applications

Aplicaciones habituales

- * Hospital communication material and packaging
- * Children's books
- * Restaurant menus
- * Packaging of personal care products
- * *Material de oficina para hospitales*
- * *Libros para niños*
- * *Menús de restaurantes*
- * *Packaging para el cuidado personal*

Properties Propiedades	Wet	Thermal	Digi-Stick	Units Unidades	Test method Métodos de ensayo
	15F138	24F238	24D238		
Thickness Espesor	15	24	24	µm	-
	0.6	1	1	Mills	
Yield Rendimiento	73.02	46.08	46	m ² /kg	Internal method Método Interno
	51 340	32 401	32 335	ln ² /Lb	
Gloss Brillo	80	55	55	%	ASTM D 2457 45°
Dyne level Tensión superficial	38	38	38	mN/m	ASTM D 2578
Coefficient of friction Coeficiente de fricción	0.25	0.25	0.25	-	Internal method Método Interno
Application temperature Temperatura de aplicación	-	95 - 115	95 - 115	°C	Internal method Método Interno
	-	200 - 240	200 - 240	°F	
Lamination strength Fuerza de laminación	-	≥ 7.5	≥ 7.5	N/25.4mm	Internal method Método Interno
	-	≥ 1.68	≥ 1.68	Lb/Inch	

*Contact us to request the certificates or additional information

*Contáctanos para solicitar los certificados o información adicional

The information provided above is based on Taghlee Industries S.L. conclusive tests and experience, which are indicative only and provided as guidelines. They do not constitute a guarantee of any specific product attributes or the suitability of products for any specific use, purpose or application. Thorough testing is recommended before running any lamination job.

La información proporcionada anteriormente se basa en las pruebas concluyentes y experiencia de Taghlee Industries S.L., que son solo indicativas y se proporcionan a título informativo únicamente. Esta información no constituye garantía de ningún atributo específico del producto o su idoneidad para un uso específico, propósito o aplicación. Se recomienda realizar pruebas exhaustivas antes de proceder con cualquier proceso de laminación.